



2# CROSSLINK PE

Property	ASTM D-3575	Result
Density (lbs/ft ³)	Suffix W	2.0
Tensile Strength, PSI	Suffix T	35
Elongation, %	Suffix T	160
Tear Resistsance	Suffix G	7.0
Compression Strength, PSI	Suffix D	
10% Deflection		4.5
25% Deflection		7.0
40% Deflection		11.0
50% Deflection		15.0
Compression Set, %	Suffix B	16.1
Thermal Stability, % Change (24 hours @ 158°F)	Suffix S	<3

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

Hanna Rubber Company
908 West 25th Street
Kansas City, Mo. 64108
P: 816-221-9600
www.hannarubber.com