

6120 Open Cell Sponge

| Property | Test Method | Result |
|-----------------------------------|-------------------------|-------------------------------|
| Density (lbs/ft ³) | ASTM D1056 | 33 |
| Thickness, inches (Tolerance) | ASTM 1056 | To 0.187 (±0.015) |
| | | $0.188 - 0.374 \ (\pm 0.030)$ |
| | | $0.375 - 0.500 \ (\pm 0.040)$ |
| | | Over 0.500 (±0.060) |
| Standard Color | | Black |
| Polymer | | Neoprene |
| Compression Force Deflection, psi | ASTM D1056 | 5 - 9 |
| | At 25% compression | |
| Compression Set, % Max | ASTM D395 | 15 |
| | 50% deflection at 158°F | |
| Accelerated Aging, % | ASTM D573 | |
| | Change in compression | ±20 |
| | deflection 168 hr. at | |
| | 158° F | |
| Oil Resistance, % Weight Change | ASTM D1056 | Medium |
| | 22 hr. at 158°F | +10 - +60 |
| Temperature | | -20°F to +175°F |
| Meets Specifications for: | | ASTM D1056-1C2 |
| | | MILC-3133-SC07 |
| | | MIL-STD-670-SC07 |

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

Hanna Rubber Company 908 West 25th Street Kansas City, Mo. 64108 P: 816-221-9600 www.hannarubber.com