



HANNA RUBBER COMPANY

Specification Sheet

HR-23 (MS #108)

Description

The 108 is a medium density cork composition product utilizing a polymeric binder system and 10/20 cork granule. Used primarily in gasket applications, the 108 conforms to ASTM F104 (F215000M1RTZ1Z2Z3).

Conformance Tests

Test Method	Physical Properties	Specification
ASTM F1315	(Zl) = Density, lbs./ft ³	17 min.
ASTM F152, Method B	(MI) = Tensile Strength, psi	100 min.
ASTM F36, Procedure F	(5) = Compressibility @ 100 psi	20 to 30%
ASTM F36, Procedure F	(Z3) = Recovery, (%)	75 minimum
ASTM F147	(T) Flexibility as received	F=5

Qualification Tests

Test Method	Physical Properties	Specification
ASTM F148, Procedure A	(R) Boiling Water, 3 hrs.	No disintegration
ASTM F148, Procedure C	(R) ASTM #1 Oil, 2 hrs. @100°C	No disintegration
ASTM F148, Procedure B	(R) Boiling 35% HCl, 1h hr.	No disintegration
ASTM F146	(Z2) ASTM Fuel A, 10 days, R.T.	No disintegration