



HANNA RUBBER COMPANY

# Specification Sheet

## NA1076

### Service Limits

Type	Description	Value
Temperature Limits	Maximum	700°F (370°C)
	Minimum	-40°F (-40°C)
	Continuous Max	392°F (200°C)
Pressure Limits	Vacuum 725 psi (50 bar)	
ASTM F104	Line Call Out	F712120-B4E99M9
Color	Black	
Available Sheet Sizes	Thickness	1/64", 1/32", 1/16", 3/32", 1/8"
	Sheet Sizes	59" x 63"
		59" x 126"

### Typical Physical Properties

ASTM Test Method	Property	Value
-	Density	106 lb/ft <sup>3</sup> (1.70 gm/cc)
F36	Compressibility	7-17%
F36	Recovery	46%
F38	Tensile Across Grain	1740 psi
F38	Creep relaxation	20%
F146	Thickness Increase After 5 Hour Immersion	
-	ASTM IRM 903 @ 300°F (150°C)	Max 30%
-	ASTM Fuel B @ 77°F (25°C)	Max 20%
F136	Weight Increase After 5 Hour Immersion	
-	ASTM Fuel B @ 77°F (25°C)	Max 20%

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.