



HANNA RUBBER COMPANY

# Specification Sheet



## Red Rubber

Red rubber is available in 36" and 48" wide rolls 1/32" – 1/4" thick (75 Durometer).

It is a low cost non-oil resistant material. It has good water resistance and resilience up to 75 durometer; compression set becomes poorer with higher durometer; generally satisfactory for most moderate chemicals and wet or dry organic acids. Not recommended for ozone, strong acids, oils, greases, fats, and most hydrocarbons.

| Property                                      | Result  |
|---|---|
| Duro Shore A $\pm$ 5                          | 75  |
| Thickness (in.)                               | 1/32 - 1/4  |
| Width (in.)                                   | 36, 48, 72  |
| Tensile Strength (psi)                        | 600   |
| Ultimate Elongation Percent                   | 150   |
| Temperature Range                             | -20°F to +200°F   |
| Estimated Weight Per Linear Foot (1/8" x 36") | 3.5 lb  |
| Specifications                                | HHG-156 Type III and ASTM D-1330 Grade I and II ASTM D 2000 2AA806A13 Z1 (Z1 =75 Durometer) |

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.