



SBR White Closed Cell Sponge

Property	Test Method	Result
Type		SBR White
Polymer		SBR
Color		White
ASTM D-1056		2A2 / 2A3
ASTM D-6576-67 Classification		RE42 / RE43
SAEJ18 APR2002		2A2 / 2A3
Density (lbs/ft ³)	ASTM D 1056	9 - 15
25% Compression Resistance (%)	ASTM D 1056	5 - 13
50% Compression Set (%)	ASTM D 1056	50
Tensile Strength	ASTM D 412 (DIE A)	100 psi
Elongation (%)	ASTM D 412 (DIE A)	175
Water Absorption (lbs/ft ²)	ASTM D 1667	0.1
Flammability	FMVSS302	Pass
Made from FDA approved ingredients	21 CFR 177.2600	

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

Hanna Rubber Company
908 West 25th Street
Kansas City, Mo. 64108
P: 816-221-9600
www.hannarubber.com