



R-10480 Medium Closed Cell Sponge

| Property | Test Method | Result |
|------------------------|-------------|--------------------|
| Polymer | | Silicone |
| Color | | Brown |
| Sheet Size | | 36" x 36" |
| ASTM D-1056 | | Type II Class A, D |
| Compression Deflection | ASTM D 1056 | 10 psi |
| Tensile Strength | ASTM D 412 | 75 psi |
| Elongation (%) | ASTM D 412 | 125% |
| Compression Set | ASTM D 1056 | 5% |
| Density | ASTM D 3574 | 29 lbs./ ft.3 |
| Water Absorption | ASTM D 1056 | < 5% |
| Temperature Range | | -100°F to +500°F |

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

- Capable of meeting AMS 3195 closed-cell specification
 - Excellent compression set resistance
 - Maintains its resiliency even under extended compression
 - Capable of meeting MIL-R-6130 Type II, Grade B and Grade C
- /ASTM D6576 Type 2, Grade B and Grade C
/MIL-R-46089
/ASTM D1056 Type 2, Class A and D

Hanna Rubber Company
908 West 25th Street
Kansas City, Mo. 64108
P: 816-221-9600
www.hannarubber.com