

Specification Sheet



Style 1152K Aramid Compression Packing

A unique packing combining 1152 and 170 fibers. Aramid corners prevent roll and extrusion. Well suited for abrasive applications and end rings with other packing's.

Temperature: To 500°F (260°C)

pH: 3-12

Speed: 2200 FPM

Pressure: To 500 PSI (35 bar) **Construction:** Interlock Braid

Comparable to: Garlock 8921K, Teadit 2003

in.	1/8″	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
ft./lb.	N/A	N/A	25	17	11.7	8.8	6.8	5.7	4.2	3.2	2.1	1.6
lbs./box	N/A	N/A	2 or 5	2 or 5	2 or 5	5	5	5	5	10	10	10

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.