



HANNA RUBBER COMPANY

Specification Sheet



Style 531 Flax Compression Packing

Style 531 flax compression packing flax fiber packing, treated with a petroleum-based lubricant and surface graphited.

Temperature: To 220°F (105°C)

pH: 5-9

Speed: 1200 FPM

Pressure: To 150 PSI (10 bar)

Construction: Square Braid

Comparable to: Chesterton 81, Crane 866, Garlock 90/131, Teadit 2177

in.	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
ft./lb.	118	58	33	22	15	11	9	7.4	5.7	3.8	2.8	2.3
lbs./box	2	2	5	5	5 or 10	5 or 10	5 or 10	5 or 10	10	10	10	10

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.