

# Garlock BLUE GYLON<sup>®</sup> 3505 BLUE GYLON For Oxygen Service

## **MATERIAL PROPERTIES**

Color: Blue Composition: PTFE with Aluminosilicate microspheres Fluid Services<sup>1</sup>: Oxygen service, moderate concentrations of acids and caustics. solvents, refrigerants, cryogenics, hydrocarbons and hydrogen peroxide Temperature<sup>2</sup>, °F (°C) Minimum: -450 (-268) Continuous Max: +500 (+260) Pressure<sup>2</sup>, Maximum, psig (bar): 800 (55) P x T (max.)<sup>2</sup>, psig x °F (bar x °C) 1/32 and 1/16": 350,000 (12,000) 250,000 (8,600) 1/8": Will Not Burn Flammability: **Bacterial Growth:** Will Not Support NSF 61 (National Sanitation Foundation), FDA (Food and Drug **Meets Specification:** 

Administration) and USP Class VI (US Pharmacopeia)

### **TYPICAL PHYSICAL PROPERTIES**

| ASTM F36          | Compressibility, %:  | 25-45                                |  |
|-------------------|--|--------------------------------------|--|
| ASTM F36          | Recovery, %:   | 30                                   |  |
| ASTM F38          | Creep Relaxation, %:   | 40.0                                 |  |
| ASTM F152         | Tensile, Across Grain, psi (N/mm²):                                  | 2000 (13.8)                          |  |
| ASTM D792         | Specific Gravity:  | 1.70                                 |  |
| <b>ASTM D1708</b> | Modulus @ 100% Elongation, psi (N/mm2):                              | 1500 (10.3)                          |  |
| ASTM F433         | Thermal Conductivity (K), W/m°K (Btu.·in./hr.·ft. <sup>2</sup> ·°F): | 0.14-0.24 (1.00-1.65)                |  |
| ASTM D149         | Dielectric Properties, range, volts/mil.                             |                                      |  |
|                   | Sample conditioning  | <u>1/16"</u>                         |  |
|                   | 3 hours at 250°F:  | 318 -                                |  |
|                   | 96 hours at 100% Relative Humidity                                   | 245 -                                |  |
| ASTM F586         | Design Factors   | <u>1/16" &amp; Under</u> <u>1/8"</u> |  |
|                   | "m" factor:  | 3.0 2.5                              |  |
|                   | "y" factor, psi (N/mm²):   | 1650 (11.4) 3000 (20.7)              |  |
| ASTM F104         | Line Call Out:   | F456999A9B7E99K3M6 <sup>(3)</sup>    |  |

#### SEALING CHARACTERISTICS

|                                | ASTM F37B   | DIN 3535- 4      |
|--------------------------------|-------------|------------------|
|                                | Fuel A      | Gas Permeability |
| Gasket Load, psi (N/mm2):      | 1000 (7)    | 4640 (32)        |
| Internal Pressure, psig (bar): | 9.8 (0.7)   | 580 (40)         |
| Leakage                        | 0.12 ml/hr. | <0.015 cc/min    |

#### Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

<sup>\*</sup> Values do not constitute specification Limits

<sup>&</sup>lt;sup>1</sup> See Garlock chemical resistance guide.

<sup>&</sup>lt;sup>2</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Hanna Rubber Company.

<sup>&</sup>lt;sup>3</sup> Increase in IRM Oil #903 (fourth numeral 9 is thickness, fifth numeral 9 is weight): Thickness = 1.0% max, Weight = 2.0% max. Sixth numberal 9: % Increase in Water: Weight = 1.0% max. A9: Leakage in Fuel A (Isooctane), Pressure = 9.8psig (0.7bar), Gasket Load = 1,000psi (7.0N/mm2): Typical = 0.12ml/hr, Max = 1.0ml/hr. E99: % Increase in ASTM Fuel B: Weight: 2.0% max., Thickness: 1.0% max.