



R-10490 Medium Closed Cell Sponge

Property	Test Method	Result
Polymer		Fluorosilicone
Color		Blue
Sheet Size		36" x 36"
ASTM D-1056		
Compression Deflection	ASTM D 1056	15 psi
Tensile Strength	ASTM D 412	180 psi
Elongation (%)	ASTM D 412	125%
Compression Set	ASTM D 1056	25%
Density	ASTM D 3574	35 lbs./ ft.3
Water Absorption	ASTM D 1056	< 5%
Temperature Range		-80°F to +400°F

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

- Capable of meeting AMS 3323
- Capable of meeting MIL-R-6130 Type 2, Grade A, B and C (excluding paragraph 4.5.7 flame resistance)
- Capable of meeting ASTM D6576 Type 2 Grade A, B and C (excluding paragraph 15 flame resistance)

Hanna Rubber Company
908 West 25th Street
Kansas City, Mo. 64108
P: 816-221-9600
www.hannarubber.com