



## NA 1000M

Compressed Sheet with NBR Binders

Service Limits		
Type	Description	Value
Temperature Limits	Maximum	720°F (390°C)
	Continuous Max	390°F (200°C)
Pressure Limits	Maximum	1450 psi (70 bar)
	Continuous Max	580 psi (50 bar)
ASTM F104	Line call out	F713230E23M6
Color		Black
Available sheet sizes	Thickness	1/64", 1/32", 1/16", 3/32", 1/8"
		Sheet Sizes

Typical Physical Properties		
Property	ASTM Test Method	Value
Density		118 lbs./ft <sup>3</sup>
Compressibility	F36	10 – 20%
Recovery	F36	Min 40%
Tensile Strength across grain	F38	2860 psi
Ignition Loss	F495	Max 37%
Thickness Increase after 5 hrs. immersion	F146	
	ASTM IRM 903 @ 300°F	Max 20%
	ASTM Fuel B @ 77°F	Max 15%
Weight increase after 5 hrs. immersion	F136	
	ASTM IRM 903 @ 300°F	Max 20%
	ASTM Fuel B @ 77°F	Max 15%

Hanna Rubber Company  
 908 West 25<sup>th</sup> Street  
 Kansas City, Mo. 64108  
 P: 816-221-9600  
[www.hannarubber.com](http://www.hannarubber.com)