



White Neoprene-EPDM- SBR-Blend

PROPERTY	TEST METHOD	RESULT
Type		SBR Blend
Polymer		SBR
Color		White
ASTM D-1056		2A2 / 2A3
ASTM D-6576-67 Classification		Type II, Grades B & C, Condition Soft-medium
SAEJ18 APR2002		2A2 / 2A3
Density (lbs/ft ³)	ASTM D 1056	6 + 2
25% Compression Resistance (%)	ASTM D 1056	7 + 2
50% Compression Set (%)	ASTM D 1056	35
Tensile Strength	ASTM D 412 (DIE A)	100 psi
Elongation (%)	ASTM D 412 (DIE A)	125
Water Absorption (lbs/ft ²)	ASTM D 1667	0.1
Flammability	FMVSS302	Pass
Made from FDA approved ingredients	21 CFR 177.2600	

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

Hanna Rubber Company
 908 West 25th Street
 Kansas City, Mo. 64108
 P: 816-221-9600
www.hannarubber.com