

## Garlock WHITE GYLON® 3540

### MATERIAL PROPERTIES\*:

<b>Color:</b>	White
<b>Composition:</b>	Microcellular PTFE
<b>Fluid Services<sup>1</sup>:</b>	Strong caustics, strong acids, chlorine, hydrocarbons, cryogenics, glass-lined equipment
<b>Temperature<sup>2</sup>, °F (°C)</b>	
Minimum:	-450 (-268)
Continuous Max:	+500 (+260)
<b>Pressure<sup>2</sup>, Maximum, psig (bar):</b>	1200 (83)
<b>P x T (max.)<sup>2</sup>, psig x °F (bar x °C):</b>	
1/32 and 1/16":	350,000 (12,000)
1/8"	250,000 (8,600)
<b>Flammability:</b>	Will Not Burn
<b>Bacterial Growth:</b>	Will Not Support
<b>Meets Specification:</b>	FDA (Food and Drug Administration)

### TYPICAL PHYSICAL PROPERTIES\*:

<b>ASTM F36</b>	<b>Compressibility, %:</b>	70-85		
<b>ASTM F36</b>	<b>Recovery, %:</b>	8		
<b>ASTM F38</b>	<b>Creep Relaxation, %:</b>	10		
<b>ASTM D149</b>	<b>Dielectric Properties, range, volts/mil.</b>			
	Sample conditioning	<u>1/16"</u>	<u>1/8"</u>	
	3 hours at 250°F:	86	61	
	96 hours at 100% Relative Humidity:	16	-	
<b>ASTM F586</b>	<b>Design Factors</b>	<u>1/16" &amp; Under</u>	<u>1/8"</u>	
	"m" factor:	3.0	3.0	
	"y" factor, psi (N/mm <sup>2</sup> )	1700 (11.7)	2200 (15.2)	
<b>ROTT</b>	<b>Gasket Constants, 3/8":</b>	Gb=550	a=0.304	Gs=7.6x10 <sup>-1</sup>

### SEALING CHARACTERISTICS\*

	<b>ASTM F37B Fuel A</b>	<b>DIN 3535-4 Gas Permeability</b>
<b>Gasket Load, psi (N/mm<sup>2</sup>):</b>	1000 (7)	4640 (32)
<b>Internal Pressure, psig (bar):</b>	9.8 (0.7)	580 (40)
<b>Leakage</b>	<b>0.25 ml/hr.</b>	<b>&lt;0.015 cc/min</b>

## Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

\* Values do not constitute specification Limits

<sup>1</sup> See Garlock chemical resistance guide.

<sup>2</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.

<sup>3</sup> Third cumeral 9: Compressibility = 70-85%. A9: Leakage in Fuel A (Isooctane), Gasket Load = 1,000psi (7.0N/mm<sup>2</sup>), Pressure = 9.8psig (0.7bar): Typical = 0.25ml/hr, Max = 1.0ml/hr.