



MODULUS DATA FOR STANDARD MATERIALS

TAN GUM 40 DUROMETER		
Test	Unit	Result
M25	PSI	67
M50		99
M100		158
NEOPRENE 50 DUROMETER		
Test	PSI	Result
M25		93
M50		138
M100		212
NEOPRENE 60 DUROMETER		
Test	PSI	Result
M25		178
M50		263
M100		364
NEOPRENE 70 DUROMETER		
Test	PSI	Result
M25		207
M50		276
M100		365