



HANNA RUBBER COMPANY

# Specification Sheet

## Food Grade (FDA/ NSF)



### Santoprene™ 241-55 TPE

Santoprene™ 241-55 TPE is manufactured by Exxon Mobil and compliant with NSF/ANSI 51 & 61 for plumbing applications in contact with potable water and food processing equipment.

Complies with FDA regulations for rubber articles intended for repeated use, as well as those in contact with non-fatty, non-oily foods as closures and sealing gaskets. Made in the USA.

**Color:** Neutral    **Finish:** Smooth    **Talc:** Talc Free Available

Samples available upon request.

Property	Result
Durometer Hardness Shore ± 5	40 to 87
Durometer Type	A
Thickness (inches)	1/16" & 1/8"
Width (inches)	36"
Tensile Strength (psi)	640 to 4000
Ultimate Elongation Percent	330 to 550
Temperature Range	-50°F to + 275°F
Estimated Weight Per Linear Foot (1/8" x 36")	1.27 lb.
Specifications	NSF/ANSI 51 & 61 Compliant

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.