

Sponge Rubber Closed Cell R-4992

Physical Property	Test Method	Result
Туре		R-4992
Polymer		EPDM / PE / IIR
Color		Gray
ASTM D-1056		2A1
ASTM D-6576-67 Classification		RE42
SAEJ18 APR2002		2A1
Density (lbs/ft ³)	ASTM D 1056	4 - 7
25% Compression Resistance (%)	ASTM D 1056	5 - 8
50% Compression Set (%)	ASTM D 1056	40
Tensile Strength	ASTM D 412 (DIE A)	40 psi
Elongation (%)	ASTM D 412 (DIE A)	225
Water Absorption (lbs/ft ²)	ASTM D 1667	0.1
Flammability	FMVSS302	Pass

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

Phone Number: 816-221-9600

Email Address: sales@hannarubber.com Website: www.hannarubber.com