



HANNA RUBBER COMPANY

Specification Sheet

Sponge Rubber Open Cell 4150

Property	Test Method	Value
Density (Average), lb/ft ³	ASTM D1056	36
Thickness, inches (Tolerance)	ASTM D1056	To 0.187 (±0.015) 0.188 - 0.374 (±0.030) 0.375 - 0.500 (±0.040) Over 0.500 (±0.060)
Standard Color		Tan
Polymer		Natural Rubber
Compression Force Deflection, psi	ASTM D1056 at 25% compression	22
Compression Set, % max.	ASTM D395 50% deflection at 158°F	
Tensile Strength, psi (Typical)	ASTM D412	
	Machine Direction	130
	Cross Machine Direction	90
Elongation, % (Typical)	ASTM D412	
	Machine Direction	90
	Cross Machine Direction	80
Accelerated Aging, %	ATSM D573 Change in compression deflection 168hr at 158°F	±20
Temperature		-20°F to 160°F
Meets Specifications For:		

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.