



HANNA RUBBER COMPANY

Specification Sheet



Style 160 Carbon Compression Packing

Style 160 carbon compression packing is a graphite filament packing impregnated with a graphite dispersion. For severe service applications where leakage must be held to a minimum. Excellent chemical resistance.

Temperature (atmosphere): To 850°F (455°C)

Temperature (steam): To 1200°F (650°C)

pH: 0-14

Speed: 4000 FPM

Comparable to: Chesterton 1/375, Crane 1625-G, Garlock G200, Teadit 2001

Pressure: Pumps-To 500 PSI (35 bar)

Pressure: Valves-To 2500 PSI (170 bar)

Construction: Interlock Braid

in.	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
ft./lb.	210	68	45	24	17	12.6	11	9.6	7.5	5.3	3.7	2.5
lbs./box	1 or 2	1 or 2	1 or 2	2	2 or 5	5	5	5	5	5 or 10	10	10

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.