

1.0 SCOPE

- 1.1 This specification describes 329 Stern-Lon Packing.
- 1.2 It is applicable for use on tail shaft liners, rudder posts, jordans, claflins, hydro-finers, shafts and rods against hot or cold water and brine to 275°F (135°C).

2.0 CONTENT AND CONSTRUCTION

2.1 Content

2.1.1 Yarn

- 2.1.1.1 329 shall be made from a single ply, twisted, long fibered roved flax yarn.

2.1.2 Lubricants

- 2.1.2.1 The finished packing shall be impregnated with a tetrafluoroethylene (TFE) dispersion.
- 2.1.2.2 The finished packing shall also be lubricated with a plasticizing break-in lubricant.
- 2.1.2.3 A final coating of finely divided fluorocarbon powder shall be embedded into the packing surface.

2.2 Construction

- 2.2.1 The packing shall be made in a square plait construction.

3.0 TYPICAL PHYSICAL, THERMAL, AND CHEMICAL PROPERTIES

3.1 Physical Properties

- 3.1.1 Maximum Service Pressure - 300 PSI (20 Bar)
- 3.1.2 Maximum Shaft Speed - 1000 FPM (5 MPS)

3.2 Thermal Properties

- 3.2.1 Maximum Service Temperature - 275°F (135°C)

3.3 Chemical Properties

- 3.3.1 Compatible pH Range - 6 to 8

A.W. CHESTERTON CO.

225 FALLON ROAD, MIDDLESEX INDUSTRIAL PARK
STONEHAM, MASSACHUSETTS 02180-9101 USA
TELEX: 94-9417 • FAX: (617) 438-8971
TEL: (617) 438-7000
CABLE: Chesterton Stoneham, Mass.