

STYLE 2044

Braided Packing, Spun Aramid Yarn, PTFE Impregnated

CONSTRUCTION:

Style 2044 is an interlock braid, using spun aramid carded yarns, treated individually with PTFE suspenoid. The packing is also lubricated with silicone based compound for quick and easy break-in. The use of spun aramid fibers produces a softer and very tough packing, but one that is less abrasive than packings braided with aramid filaments.

APPLICATION / SERVICE:

Style 2044 is a durable packing able to withstand granular and abrasive applications. It is recommended for service in superheated steam, slurries, petroleum derivatives, solvents, chemicals, liquified gases, pulp and paper stocks, sugar syrups, and other abrasive fluids.

For a firmer aramid/PTFE packing, with higher pressure capabilities, see Style 2004.

SERVICE LIMITS:

Temperature Limits		Pressure Limits	
Minimum	-148°F (-100°C)	Static	2200 psi (150 bar)
Maximum	536°F (280°C)	Rotating	290 psi (20 bar)
		Reciprocating	1150 psi (80 bar)
Shaft Speed	2950 fpm (15 m/s)	pH	2-12



APPROXIMATE STANDARD PACKAGE (±10%):

Size	Ft/Lb	91.02	40.45	23.49	15.42	10.66	8.07	6.16	4.86	3.93	2.73	2.02	1.54
	Inch	1/8	3/16	1/4	5/16	3/8	7/16	1/2	9/16	5/8	3/4	7/8	1
Standard Package (±10%)		1 Lb (0.5 Kg)	2 Lbs (1 Kg)	5 Lbs (2 Kg)				10 Lbs (5 Kg)					

Properties and application parameters shown throughout this data sheet are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult TEADIT. Failure to select proper sealing products could result in property damage and/or serious personal injury. Specifications are subject to change without notice; this edition cancels all previous issues.

Teadit North America.

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - www.teadit-na.com