



HANNA RUBBER COMPANY

Specification Sheet

Branded Vellumoid

Treated cellulose fiber material impregnated with a protein glue and glycerin binder. General purpose gasket material. Service temperatures up to 250°F. UL listed.

PROPERTIES	
Compressibility % @ 6.89 MP's (1000 psi)	25-40
Minimum Recovery %	40
Tensile Strength Minimum %	2000
ASTM Oil No. 3 Thickness Increase Maximum %	5
Weight Increase Maximum %	15
ASTM Fuel B Thickness Increase Maximum %	5
Weight Increase Maximum %	15
Distilled Water Thickness Increase Maximum %	30
Weight Increase Maximum %	90