



HANNA RUBBER COMPANY

Specification Sheet

Sponge Rubber Open Cell 2110

Physical Property	Test Method	Result
Polymer		Natural Rubber
Color		White
Density (lbs/ft ³)	ASTM D 1056	27
Thickness, inches (Tolerance)	ASTM D 1056	0.250 (±0.050)
Compression Deflection (25%), psi	ASTM D 1056	8 - 12
Compression Deflection Change After Oven Aging, %	ASTM D 1056 168 hrs at 158°F	± 20
Compression Set, % max	ASTM D 1056 50% deflection at 158° F	15
Temperature Range		-20° F to +158°F
FDA 21 CFR 177 2600		

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.