



HANNA RUBBER COMPANY

Specification Sheet

Velbuna WG-25

A blended rubber and cellulose fiber medium density beater addition material. Demonstrates good resistance to oils, water coolants and salt solutions at service temperatures up to 300° F.

PROPERTIES	
Compressibility % @ 6.89 MP's (1000 psi)	15-30
Minimum Recovery %	40
Tensile Strength Minimum %	1700
ASTM Oil No. 3 Thickness Increase Maximum %	10
Weight Increase Maximum %	65
ASTM Fuel B Thickness Increase Maximum%	15
Weight Increase Maximum %	65
Distilled Water Thickness Increase Maximum%	40
Weight Increase Maximum %	80