



HANNA RUBBER COMPANY

Specification Sheet

Velbuna WG-57-G

An economical low density cellulose and styrene butadiene rubber beater addition material. WG-57-G is a tough, versatile material intended for applications where a low cost beater addition type material is indicated at service temperatures up to 350° F.

PROPERTIES	
Compressibility % @ 6.89 MP's (1000 psi)	15-35
Minimum Recovery %	35
Tensile Strength Minimum %	1500
ASTM Oil No. 3 Thickness Increase Maximum %	15
Weight Increase Maximum %	70
ASTM Fuel B Thickness Increase Maximum%	15
Weight Increase Maximum %	70
Distilled Water Thickness Increase Maximum%	55
Weight Increase Maximum %	80