



**HANNA RUBBER COMPANY**

# Specification Sheet

## 2 LB EVA

Tests Performed	Test Method	Typical Results
Density	ASTM D 3575(W)	1.7-2.25 lb/ft <sup>3</sup>
Tensile Strength	ASTM D 3575(T)	40-60 psi
Tear Resistance	ASTM D 3575(G)	9-13 lb/in
Elongation	ASTM D 3575(T)	260-320 %
Compression Set	ASTM D 3575(B)	<20 %
Compression Strength 25%	ASTM D 3575(D)	7-11 psi
Compression Strength 50%	ASTM D 3575(D)	14-20 psi
Thermal Stability	ASTM D 3575(S)	<3 %
Water Absorption	ASTM 1667	0.128 lbs/sft
Working Temperature	RANGE	-40 – 185F

Does not contain lead, cadmium, mercury or formaldehyde, and meets the global REACH and RoHS requirements covering prohibited substances. Will meet UL94-HB.

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.