



HANNA RUBBER COMPANY

Specification Sheet

4 LB EVA

Standard Test	ASTM D-3575	
Density, lb/cu ft	Suffix W	4.0
Tensile Strength, PSI	Suffix T	97
Elongation, %	Suffix T	375
Tear Resistance, lbs/in	Suffix G	19
Compression Strength, psi	Suffix D	
-25% Deflection		13
-50% Deflection		22
Compression Set, %	Suffix B	11
Thermal Stability, % Change (24 hours @ 158° F)		< 8

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.