




HANNA RUBBER COMPANY

Specification Sheet

Coiled FEP Tubing

- Made of chemically inert clear FEP
- Manufactured from FDA compliant materials
- Heat set into a retractable coil; excellent recoil memory



Physical Properties	FEP
Hardness, Shore D	55-60
Tensile Strength, psi	2800-5000
Elongation at Break, %	250-330
Brittle Temperature^^	-450°F
Minimum Operating Temperature for Tubing^^	-100°F
Maximum Operating Temperature for Tubing^^	200°F

A. ID (in.)	B. OD (in.)	C. Tail Length (in.)	D. OD of Coil (in.)	E. Expanded Length
1/16	3/16	6	1.125	12, 24, 48, 72
1/8	1/4	6	1.5	12, 24, 48, 72
3/16	5/16	6	2.25	12, 24, 48, 72
1/4	3/8	6	2.375	12, 24, 48, 72
3/8	1/2	6	4	12, 24

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.