



HANNA RUBBER COMPANY

Specification Sheet



Colored Polyurethane Tubing

Physical Properties	
Hardness, Shore A ± 2	85
Tensile Strength, psi	5500
Elongation at Break, %	580
Brittle Temperature	-90°F
Max. Operating Temperature	175°F

Product Number	ID (in.)	OD (in.)	Wall (in.)	Working PSI (at 70°F)	Burst PSI (at 70°F)	Opacity	Colors
16-2110528	.063 (1/16)	.125 (1/8)	.031 (1/32)	135	405	Opaque	Black
16-2110535	.063 (1/16)	.125 (1/8)	.031 (1/32)	135	405	Transparent	Blue
16-2110563	.063 (1/16)	.125 (1/8)	.031 (1/32)	135	405	Transparent	Green
16-2110605	.063 (1/16)	.125 (1/8)	.031 (1/32)	135	405	Transparent	Red
16-2110619	.063 (1/16)	.125 (1/8)	.031 (1/32)	135	405	Opaque	White
16-2110626	.063 (1/16)	.125 (1/8)	.031 (1/32)	135	405	Transparent	Yellow
16-2111158	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Opaque	Black
16-2111165	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Transparent	Blue
16-2111193	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Transparent	Green
16-2111200	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Opaque	Gray
16-2111221	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Opaque	Orange
16-2111235	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Transparent	Red
16-2111249	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Opaque	White
16-2111256	.125 (1/8)	.250 (1/4)	.063 (1/16)	130	390	Transparent	Yellow

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.