



HANNA RUBBER COMPANY

Specification Sheet



Medical Grade Silicone Tubing

Physical Properties	
Hardness, Shore A ± 5	60A
Tensile Strength, psi	1200
Elongation at Break, %	425
Brittle Temperature	-100
Maximum Operating Temperature	400

Product Number	ID (in.)	OD (in.)	Wall (in.)	Available Lengths (ft.)	Colors
16-2810304	.030	.065	.018	50	Natural
16-2810381	.031 (1/32)	.156 (5/32)	.063 (1/16)	50	Natural
16-2810458	.040	.085	.023	50	Natural
16-2810689	.063 (1/16)	.125 (1/8)	.031 (1/32)	50	Natural
16-2810766	.063 (1/16)	.188 (3/16)	.063 (1/16)	50	Natural
16-2810843	.078 (5/64)	.125 (1/8)	.024	50	Natural
16-2810920	.104	.192	.044	50	Natural
16-2810997	.125 (1/8)	.250 (1/4)	.063 (1/16)	50	Natural
16-2811151	.188 (3/16)	.313 (5/16)	.063 (1/16)	50	Natural
16-2811228	.188 (3/16)	.375 (3/8)	.094 (3/32)	50	Natural
16-2811305	.250 (1/4)	.375 (3/8)	.063 (1/16)	50	Natural
16-2811382	.250 (1/4)	.438 (7/16)	.094 (3/32)	25	Natural
16-2811459	.250 (1/4)	.500 (1/2)	.125 (1/8)	25	Natural
16-2811536	.313 (5/16)	.438 (7/16)	.063 (1/16)	25	Natural
16-2811613	.313 (5/16)	.500 (1/2)	.094 (3/32)	25	Natural
16-2811690	.375 (3/8)	.500 (1/2)	.063 (1/16)	50	Natural
16-2811844	.375 (3/8)	.625 (5/8)	.125 (1/8)	25	Natural
16-2811921	.500 (1/2)	.625 (5/8)	.063 (1/16)	25	Natural

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.