



HANNA RUBBER COMPANY

Specification Sheet



PFA Tubing

Physical Properties	
Hardness, Shore D	55-60
Tensile Strength, psi	4200
Elongation at Break, %	400
Brittle Temperature	<-450°F
Max. Continuous Op. Temp.	500°F

Product Number	ID	OD	Wall	Working PSI (at 72°F)	Burst PSI (at 72°F)
3200176	.063 (1/16)	.125 (1/8)	.030	449	2245
3200330	.094 (3/32)	.156 (5/32)	.030	360	1800
3200407	.125 (1/8)	.188 (3/16)	.030	299	1495
3200484	.125 (1/8)	.250 (1/4)	.063 (1/16)	464	2320
3200561	.188 (3/16)	.250 (1/4)	.030	225	1125
3200715	.250 (1/4)	.313 (5/16)	.030	179	895
3200792	.250 (1/4)	.375 (3/8)	.063 (1/16)	310	1550
3200869	.313 (5/16)	.375 (3/8)	.030	140	700
3201100	.375 (3/8)	.500 (1/2)	.063 (1/16)	230	1150
3201331	.500 (1/2)	.563 (9/16)	.030	88	440
3201408	.500 (1/2)	.625 (5/8)	.063 (1/16)	186	930
3201716	.625 (5/8)	.750 (3/4)	.063 (1/16)	140	700
3210354	4mm	6mm	1mm		
3210529	6mm	8mm	1mm		
3210704	8mm	10mm	1mm		
3210879	10mm	12mm	1mm		

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.