



HANNA RUBBER COMPANY

# Specification Sheet

## HR-22 (MS #107)

### Description

The 107 is a low density cork composition product utilizing a polymeric binder system and 10/20 cork granule. Used primarily in gasket applications, the 107 conforms to ASTM F104 (F217000M9RTZ1Z2).

### Conformance Tests

Test Method	Physical Properties	Specification
ASTM F147	(T) Flexibility as received	F=S
ASTM F1315	(Z1) = Density, lbs./ft <sup>3</sup>	14 min.
ASTM F152, Method B	(M9) = Tensile Strength, psi	75 min.
ASTM F36, Procedure F	(7) = Compressibility @ 100 psi	30 to 50%
ASTM F36, Procedure F	(Z2) = Recovery, (%)	80 minimum

### Qualification Tests

Test Method	Physical Properties	Specification
ASTM F148, Procedure A	(R) Boiling Water, 3 hrs.	No disintegration
ASTM F148, Procedure C	(R) ASTM #1 Oil, 2 hrs. @100°C	No disintegration
ASTM F148, Procedure B	(R) Boiling 35% HCl, 1h hr.	No disintegration