



HANNA RUBBER COMPANY

Specification Sheet

Black TPR Tubing



Physical Properties	
Hardness, Shore A @ 77°F, ±5	64
Tensile Strength @ 77°F, psi	1000
Elongation at Break, %	400
Tear Strength @ 73°F, pli	140
Compression Set % @	
73°F after 168 hrs.	22
212°F after 168 hrs.	34
Brittle Temperature, °F	<-76
Minimum Recommended	
>Operating Temp., °F	-60
Maximum Recommended	
Operating Temperature, °F	275

Product Number	ID (in.)	OD (in.)	Wall (in.)	Available Lengths (ft.)	Shore Hardness(±5)
4610228	.125 (1/8)	.250 (1/4)	.063 (1/16)	50	64A
4610396	.188 (3/16)	.313 (5/16)	.063 (1/16)	50	64A
4610564	.250 (1/4)	.375 (3/8)	.063 (1/16)	50	64A
4610620	.250 (1/4)	.500 (1/2)	.125 (1/8)	50	64A
4610676	.313 (5/16)	.438 (7/16)	.063 (1/16)	50	64A
4610844	.375 (3/8)	.500 (1/2)	.063 (1/16)	50	64A
4610956	.375 (3/8)	.625 (5/8)	.125 (1/8)	50	64A
4611180	.500 (1/2)	.625 (5/8)	.063 (1/16)	50	64A
4611292	.500 (1/2)	.750 (3/4)	.125 (1/8)	50	64A
4611628	.625 (5/8)	.875 (7/8)	.125 (1/8)	50	64A

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.