



## R-10450 Closed Cell Sponge

Property	Test Method	Result
Polymer		Silicone
Color		Blue / Gray
Sheet Size		36" x 36"
ASTM D-1056		
Compression Deflection	ASTM D 1056	15 psi
Tensile Strength	ASTM D 412	125 psi
Elongation (%)	ASTM D 412	< 10%
Compression Set	ASTM D 1056	25%
Density	ASTM D 3574	35 lbs./ ft.3
Water Absorption	ASTM D 1056	< 5%
Temperature Range		-100°F to +500°F

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

- Reinforced for excellent tensile strength
- Eliminates outward extrusion under pressure
- Wide range of temperature use

Hanna Rubber Company  
908 West 25<sup>th</sup> Street  
Kansas City, Mo. 64108  
P: 816-221-9600  
[www.hannarubber.com](http://www.hannarubber.com)