



HANNA RUBBER COMPANY

Specification Sheet

Vellutherm 611

A nonasbestos beater addition material consisting of a unique blend of fibers and other components with a cured nitrile rubber binder. Vellutherm 611 demonstrates high compressive strength and excellent dimensional stability under varying ambient humidities at service temperatures up to 350° F.

PROPERTIES	
Compressibility % @ 35.5 MP's (5000 psi)	10-20
Minimum Recovery %	50
Tensile Strength Minimum %	2000
ASTM Oil No. 3 Thickness Increase Maximum %	10
Weight Increase Maximum %	30
ASTM Fuel B Thickness Increase Maximum%	15
Weight Increase Maximum %	30
Distilled Water Thickness Increase Maximum%	
Weight Increase Maximum %	